

arovex™

Product Line: Arovex 180

Introduction

Arovex 180 is a 180°F cure, carbon nanotube strengthened prepreg system suitable for numerous composites applications.

Available in widths up to 60 inches for standard woven fabrics. Unitape widths up to 24 inches in 80 gsm to 300 gsm.

The carbon nanotube enhancement makes Arovex a high strength and high stiffness prepreg system. It also processes as easily as conventional prepreps and has a long out-life for easier handling and processing.

Features

Enhanced mechanical properties with a medium tack. Strengthened with an optimum level of carbon nanotubes for additional toughness. 30 day out-life at 72°F, one year at 0°F. Available with most commercial woven fabrics, and a large range of unidirectional fibers.

Processes

Vacuum bagged, oven cured
Hot press

Applications

Carbon
E-Glass
S-Glass
Aramid
Other fabrics on request



Characteristics¹

Arovex tested with Toho G30-700 fiber with a resin content of 38% (others available) Cured 10 hours @ 180 F and 14 psi vacuum.

Test	Test Method	Value
0° Flexural Strength	ASTM D 0790	201 (ksi)
0° Flexural Modulus	ASTM D 0790	16.4 (Msi)
90° Flexural Strength	ASTM D 0790	9.9 (ksi)
90° Flexural Modulus	ASTM D 0790	1.32 (Msi)
Short Beam Shear Strength	ASTM D 5528-07	11.5 (ksi)
0° Tensile Strength	ASTM D 3039	259 (ksi)
0° Tensile Modulus	ASTM D 3039	19.2 (Msi)
0° Compressive Strength	SACMA SRM 1R-94	175 (ksi)
0° Compressive Modulus	SACMA SRM 1R-94	18.5 (Msi)
G _{Ic} Strain Energy Release	ASTM D 5528-07	3.0 (in-lb/in²)

Mechanical data obtained by independent third party testing. Values normalized to 60% fiber volume. Values are typical and are not intended as a specification value

¹ Typical characteristics and properties, not to be used as specifications.

Prepreg Storage Life

Tack life: 21 days @ 72 F
Out life: 30 days @ 72 F
Shelf life: 1 year @ 0 F

Recommended Cure

Temperature ramp 2 – 7 F per minute to 180 F. Hold at 180 F for ten hours, cool to < 140 F. Vacuum pressure is at 21 inches mercury.

Safety & Handling

Zyvex Performance Materials (ZPM) provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, and use information.

ZPM encourages its customers to review the **Arovex** MSDS prior to use.

Contact Information

General information	877-469-9839 614-481-2222
Sales & Technical Service	614-481-2207
Health & Safety	614-481-2208
Online	www.zyvexpro.com
Mail	Zyvex Performance Materials 1255 Kinnear Rd. Ste 100 Columbus, OH 43212

arovex™

ZPM makes no warranty or guarantee, either express or implied, concerning the results of any Arovex in a customer's application. All information and technical assistance given by ZPM is also without warranty or guarantee. The customer is responsible for any and all testing to determine if Arovex is useful in their application and that its use does not infringe upon any valid patents.

Applications and Processes listed are only suggestions; other applications and processes are possible.

All products are sold pursuant to ZPM standard terms and conditions. It is expressly understood and agreed that the customer assumes and releases ZPM from all liability, in tort, contract, or otherwise incurred in connection with the use, results, health & safety effects, handling, and disposal of Epovex epoxy. Nothing herein shall be construed as a recommendation to use an Epovex epoxy in conflict with any patents or other intellectual property.

Arovex is a trademark of Zyvex Performance Materials.

© 2010 Zyvex Performance Materials, LLC. All rights reserved.

